

Facestock

A blue woodfree machine finished paper.

Basis Weight	80 g/m ²	ISO 536
Caliper	107 µm	ISO 534

Adhesive

A general purpose permanent, acrylic based adhesive.

Liner

Hygroflat 55, a one side coated, bleached kraft paper.

Basis Weight	55 g/m ²	ISO 536
Caliper	58 µm	ISO 534

Laminate

Total Caliper	181 µm±10%	ISO 534
---------------	------------	---------

Performance data

Initial Tack	17 N/25mm	FTM 9 Glass
Peel Adhesion 90°	7 N/25mm	FTM 2 St.St.
Min. Application Temp.	0 °C	
Service temperature	-20°C to 80°C	

Adhesive Performance

The adhesive is characterized by a high initial tack, excellent adhesion and good low temperature performance on a wide variety of substrates.

Applications and use

The product is ideal for label applications using variable information such as address, instruction and inventory labels, labels for office use and many other applications. The product has tightly defined release characteristics to avoid predisping during the printing or copying process. The well balanced laminate construction ensures optimum layflatness during conversion and end-use under a relatively wide range of conditions.

The hygroflat backing paper is specially suited to the more critical refolding demands of high-speed computer printers, providing optimum layflatness and excellent interfolding characteristics.

Conversion & printing

The facestock's surface structure provides excellent toner bonding and print resolution .LASERCOPY BLUE is specially designed for the manufacturer of A4 sheets for use in; medium speed laser printers, desk-top laser printers, dry toner copiers. The Backing paper can be printed with conventional printing methods.

Special Approvals

The adhesive complies with the European food directives and legislations, FDA 175.105 and the German recommendations XIV as published by BfR. BfR (Bundesinstitut für Risikobewertung) is the German Federal Institute for Risk Assessment. The adhesive can be used in direct contact with dry, non fatty foodstuffs.


Shelf life

Two years under storage conditions as defined by FINAT (20-25°C; 40-50%RH)

AA376

Fasson®

LASERCOPY BLUE - S2012HTC-HF55



LASERCOPY BLUE



S2012HTC



HF55



This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.

If you would like to make a suggestion or comment on this datasheet, please send an email to datasheet.mgmt@eu.averydennison.com

Avery Dennison Materials Group Europe

Willem Einthovenstraat 11
2342 BH Oegstgeest
The Netherlands
+31 (0)85 000 2000

Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>



©2016 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.