Facestock

A white, machine coated, woodfree printing paper specially treated to give good resistance to grease and oil.

 $\begin{array}{cccc} \text{Basis Weight} & 90 \text{ g/m}^2 & \text{ISO 536} \\ \text{Caliper} & 90 \text{ } \mu\text{m} & \text{ISO 534} \\ \end{array}$

Adhesive

A special purpose permanent, acrylic based adhesive for direct food contact.

Liner

BG40 white, a supercalendered glassine paper.

 $\begin{array}{ccc} \text{Basis Weight} & 60 \text{ g/m}^2 & \text{ISO 536} \\ \text{Caliper} & 53 \text{ } \mu\text{m} & \text{ISO 534} \\ \end{array}$

Laminate

Total Caliper 167 µm±10% ISO 534

Performance data

Initial Tack 10 N/25mm FTM 9 Glass Peel Adhesion 90° 6.5 N/25mm FTM 2 St.St.

Min. Application Temp. -15 °C
Service temperature -50 °C to 70 °C

Applications and use

Typical applications include labels for food packaging and applications where contact with oils and greases are expected. Special care should be given during dispensing around the gum free area

Conversion & printing

The product can be printed by letterpress, flexo, gravure, screen and hot-foil stamping.

The special product lay-out could have an influence on conversion speed

Special Approvals


In accordance with the requirements of relevant EU food regulations, the adhesive S2800 may safely stand in direct contact with dry, moist and non-fatty foodstuffs.

Shelf life

Two years under storage conditions as defined by FINAT (20- 25° C; 40- 50° RH)


AA665

Fasson ® GREASEPROOF - S2800 INC SGP-BG40WH



GREASEPROOF

S2800



This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.

If you would like to make a suggestion or comment on this datasheet, please send an email to datasheet.mgmt@eu.averydennison.com

Avery Dennison Materials Group Europe

Willem Einthovenstraat 11 2342 BH Oegstgeest The Netherlands +31 (0)85 000 2000

Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see http://terms.europe.averydennison.com



©2016 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.