

Facestock

A specially 'non - phosphorescent' coated semi-gloss white 'quality' printing paper with water soluble back coating. This paper has been developed specifically for printing postage stamps and readily accepts cancelation inks.

The facestock is made from FSC® certified paper (FSC Mix Credit, chain-of-custody number: CU-COC-807907, Licence Code: C004451).

Basis Weight	96 g/m ²	ISO 536
Caliper	85 µm	ISO 534

Adhesive

A general purpose permanent, acrylic based adhesive.

Liner

Hygroflat 80, a one side coated, bleached kraft paper.

Basis Weight	80 g/m ²	ISO 536
Caliper	78 µm	ISO 534

Laminate

Total Caliper	179 µm±10%	ISO 534
---------------	------------	---------

Performance data

Initial Tack	16 N/25mm	FTM 9 Glass
Peel Adhesion 90°	9 N/25mm	FTM 2 St.St.
Min. Application Temp.	5 °C	
Service temperature	-20°C to 80°C	

Adhesive Performance

The adhesive is characterized by a high initial tack, excellent adhesion and good low temperature performance on a wide variety of substrates.

Applications and use

The hygroflat backing paper is generally suited to the refolding demands of high-speed computer printers, providing optimum layflatness and excellent interfolding characteristics. A decurling bar might be needed for optimal results.

Conversion & printing

The facestock's smooth semi-gloss surface offers excellent print quality by all conventional printing technologies particularly gravure and litho.

Special Approvals

The adhesive complies with the European food directives and legislations, FDA 175.105 and the German recommendations XIV as published by BfR. BfR (Bundesinstitut für Risikobewertung) is the German Federal Institute for Risk Assessment. The adhesive side may stand in direct contact with dry, moist and such fatty foodstuffs which have a correction factor of at least 3 according to the Regulation (EU) No 10/2011.

The liner is made from FSC® certified paper (FSC Mix Credit, chain-of-custody number: CU-COC-807907, Licence Code: FSC-C004451).


Shelf life

Two years under storage conditions as defined by FINAT (20-25°C; 40-50%RH)

AC099

Fasson®

STAMP96 NPW FSC - S2000N-HF80
FSC



STAMP96 NPW FSC

S2000N

HF80 FSC

This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.

If you would like to make a suggestion or comment on this datasheet, please send an email to datasheet.mgmt@eu.averydennison.com

Avery Dennison Materials Group Europe

Willem Einthovenstraat 11
2342 BH Oegstgeest
The Netherlands
+31 (0)85 000 2000

**Warranty**

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>

©2016 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.