

### Facestock

A clear bi-axially oriented, polypropylene film with a print-receptive topcoat.

Basis Weight	46 g/m <sup>2</sup>	ISO 536
Caliper	50 µm	ISO 534

### Adhesive

A super-clear, solvent acrylic based permanent adhesive.

### Liner

A clear polyester liner giving optimum smoothness to the adhesive layer.

This liner is 100% recyclable. Visit our website or send an email to [linerrecycling@eu.averydennison.com](mailto:linerrecycling@eu.averydennison.com) for more information.

Basis Weight	32 g/m <sup>2</sup>	ISO 536
Caliper	23 µm	ISO 534

### Laminate

Total Caliper	90 µm±10%	ISO 534
---------------	-----------	---------

### Performance data

Initial Tack	12.5 N/25mm	FTM 9 Glass
Peel Adhesion 90°	9.5 N/25mm	FTM 2 St.St.
Min. Application Temp.	10 °C	
Service temperature	-40°C to 115°C	

### Adhesive Performance

S517N provides high adhesion to glass containers and could be used in pasteurisation process.

### Applications and use

Applications are predominantly in market segments where rigid containers are used (e.g. Glass, PET). Due to fairly rigid nature of the film, care should be taken with use on non-uniform surfaces and where a high level of squeezability is desired. Automatic application: The robust film liner allows for consistent, snap free, application on high speed lines.

### Conversion & printing

The modified acrylic based topcoating can be printed by conventional printing techniques including flexo, screen, offset, letterpress, silkscreen, gravure, and hot or cold foiling processes. UV, water-based and solvent-based inks can be used. The topcoat is designed for optimal ink adhesion. On-press corona treatment is not advised. The face material is suitable for Thermal Transfer printing. Exact inks, foils and ribbons should be specified by your ink/foil/ribbon supplier. The material has very good register properties especially when a high number of different colours are used.

As the liner is transparent, the applicator must detect the print itself or registration marks must be provided on either face or liner.

Press stability is good with stable, consistent register during conversion. Flat bed performance is good while solid and magnetic rotary dies need additional care. (Die bearers must be adjusted to the polyester liner).

### Shelf life

Two years under storage conditions as defined by FINAT (20-25°C; 40-50%RH)

## AF205

### Fasson®

PP LIGHT TOP CLEAR - S517N-PET23



PP50 TOP CLEAR

S517N

PET23

*This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.*

*If you would like to make a suggestion or comment on this datasheet, please send an email to [datasheet.mgmt@eu.averydennison.com](mailto:datasheet.mgmt@eu.averydennison.com)*

**Avery Dennison Materials Group Europe**

Willem Einthovenstraat 11  
2342 BH Oegstgeest  
The Netherlands  
+31 (0)85 000 2000

**Warranty**

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>



©2016 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.