

### Facestock

A white woodfree, thermal coated paper, with a top and backside protective coating. The black imaging thermosensitive coating providing very good resistance to moisture, fat, oil, alcohol, etc. The facestock is made from FSC® certified paper (FSC Mix Credit, chain-of-custody number: CU-COC-807907, Licence Code: C004451).

Basis Weight	75 g/m <sup>2</sup>	ISO 536
Caliper	74 µm	ISO 534
Max Print Speed	250 mm/sec	
Image Density (Typical)	1.3 odu	

### Adhesive

A general purpose removable, rubber based adhesive.

### Liner

BG40 brown, a supercalendered glassine paper.

Basis Weight	55 g/m <sup>2</sup>	ISO 536
Caliper	49 µm	ISO 534

### Laminate

Total Caliper	143 µm±10%	ISO 534
---------------	------------	---------

### Performance data

Initial Tack	5 N/25mm	FTM 9 Glass
Peel Adhesion 90°	2.5 N/25mm	FTM 2 St.St.
Min. Application Temp.	-20 °C	
Service temperature	-40°C to 70°C	

### Adhesive Performance

The adhesive is suitable for general application on a wide range of substrates, featuring good initial tack and adhesion combined with excellent removability. Remark: Application to porous substrates such as paper and board, or prolonged exposure to UV light may adversely affect clean removability.

### Applications and use

This Direct Thermal product is designed for use where good resistance to oil, water and plasticizer over an extended period is required. Continuous exposure to an assortment of chemicals or continuous wet immersion will eventually cause image fading.

### Conversion & printing

The product can be converted by all conventional roll conversion technologies including flexographic and UV letter press. However, due to the thermographic properties, exposure above 50°C may cause premature imaging or discoloration. It is advisable to test inks and varnishes before conversion.

We generally recommend not to pre-print the label area that needs to be thermally printed.

### Special Approvals

The adhesive complies with the European food directives and legislations, FDA 175.105 and the German recommendations XIV as published by BfR. BfR (Bundesinstitut für Risikobewertung) is the German Federal Institute for Risk Assessment. The adhesive can be used in direct contact with dry and moist, non fatty foodstuffs.


### Shelf life

One year under storage conditions as defined by FINAT (20-25°C; 40-50%RH)

## AG291

## Fasson®

### THERMAL TOP S8 FSC - R5100-BG40BR



THERMAL TOP S8 FSC

R5100

BG40BR

*This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. The actual front and liner used might influence adhesive values. Further testing is always recommended.*

*If you would like to make a suggestion or comment on this datasheet, please send an email to [datasheet.mgmt@eu.averydennison.com](mailto:datasheet.mgmt@eu.averydennison.com)*

**Avery Dennison Materials Group Europe**

Willem Einthovenstraat 11  
2342 BH Oegstgeest  
The Netherlands  
+31 (0)85 000 2000

**Warranty**

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>



©2019 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.