

Material

A white, one side machine coated, supercalendered woodfree printing paper with semi-gloss appearance.

Basis Weight	62 g/m ²	ISO 536
Caliper	54 µm	ISO 534
Tensile Str. MD	4.4 kN/m	ISO 1924-2
Tensile Str. CD	2.2 kN/m	ISO 1924-2
Tear str. MD	350 mN	ISO 1974
Tear str. CD	400 mN	ISO 1974
Elongation MD	2 %	ISO 1924-2
Elongation CD	5.4 %	ISO 1924-2
Gloss 75° angle	74 %	T480
Opacity	85 %	ISO 2471
Brightness	86 %	ISO 2470

Applications and use

This product is suitable for a wide range of promotional and industrial label applications where attractive semi-gloss appearance in multi-colour work is required.

Conversion & printing

This product is suitable for solid and halftone images and text printing by letterpress, flexo (UV and waterbased) offset and screen processes. Hot and cold foil stamping, varnishing and variable imprinting with thermal transfer are also suitable for this product.


Shelf life

One year under storage conditions as defined by FINAT (20-25°C; 40-50%RH)

AG394

Fasson ®

MC PRIMECOAT 1S-60



MC PRIMECOAT 1S-60

This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.

If you would like to make a suggestion or comment on this datasheet, please send an email to datasheet.mgmt@eu.averydennison.com

Avery Dennison Materials Group Europe

Willem Einthovenstraat 11
2342 BH Oegstgeest
The Netherlands
+31 (0)85 000 2000

Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes.

Avery Dennison products are warranted to be free of defects in material or workmanship for a period of one year from the date of shipment. Should a defect be communicated to Avery Dennison within that time frame, Avery Dennison will evaluate and determine the existence of the defect and further decide, at its sole discretion, to either replace the defective product without charge or compensate it with a credit note in such amount as Avery Dennison deems reasonable. Avery Dennison shall have no responsibility beyond the replacement value of the defective product nor shall in any way be liable or responsible for consequential or incidental damages.



ANY OTHER WARRANTY, WHETHER EXPRESS OR IMPLIED, OR WHETHER OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE OR OTHERWISE, SHALL BE EXCLUDED. NO WAIVER, ALTERATION, ADDITION OR MODIFICATION OF THE FOREGOING CONDITIONS SHALL BE VALID UNLESS MADE IN WRITING AND SIGNED BY AN EXECUTIVE OFFICER OF AVERY DENNISON.

©2013 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.