

### Facestock

White polyethylene film with top coating and special 'void' effect.

Basis Weight	89 g/m²	ISO 536
Caliper	90 µm	ISO 534

#### Adhesive

An extra permanent, acrylic based adhesive.

#### Liner

BG45 white, a supercalendered glassine paper.

Basis Weight	73 g/m²	ISO 536
Caliper	62 µm	ISO 534
Transparency	50 %	DIN 53147
Laminate		
Total Caliper	170 µm±10%	ISO 534
Performance data		
Initial Tack	17 N/25mm	FTM 9 Glass
Peel Adhesion 90°	10 N/25mm	FTM 2 St.St.
Min. Application Temp.	5 °C	
Service temperature	-40°C to 90°C	

#### Adhesive Performance

S700 is a reinforced permanent acrylic based adhesive with very good initial tack and adhesion to a wide range of substrates.

#### Applications and use

Once applied to the substrate on removal, an irreversible and dry "void" fooprint message - will detach itself from the face film. Labels which have been removed cannot be reapplied since repositioning will leave visible proof that tampering has taken place.

The flexible front is adapted for perfect tamper evident effect on corners and irregular shapes

#### **Conversion & printing**

Can be printed by all conventional printing technologies including water-based flexo, letterpress and UV-screen and thermal transfer.


#### Shelf life

One year under storage conditions as defined by FINAT (20- $25^{\circ}C$ ; 40-50%RH)

# AM825

Fasson ®

# PE85 VOID MATT WHITE - S700-BG45WH



# PE85 VOID MATT WHITE

S700

BG45WH

This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. The actual front and liner used might influence adhesive values. Further testing is always recommended.

If you would like to make a suggestion or comment on this datasheet, please send an email to datasheet.mgmt@eu.averydennison.com

## Avery Dennison Materials Group Europe

Willem Einthovenstraat 11 2342 BH Oegstgeest The Netherlands +31 (0)85 000 2000

Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see



©2019 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery



http://terms.europe.averydennison.com

Dennison.