Facestock

A bright white semi-gloss coated card. The facestock is made with FSC certified pulp (FSC Mix Credit, chain-of-custody number: CU-COC-807907).

Basis Weight 130 g/m 2 ISO 536 Caliper 96 μm ISO 534

Adhesive

A permanent, rubber based adhesive.

Liner

BG40 brown FSC certified, supercalendered glassine paper.

Laminate

Total Caliper 160 µm±10% ISO 534

Performance data

Initial Tack 22 N/25mm FTM 9 Glass Peel Adhesion 90° 14 N/25mm FTM 2 St.St.

Min. Application Temp. 5 °C

Service temperature -40°C to 70°C

Adhesive Performance

The adhesive features excellent tack and adhesion on a wide variety of substrates, including apolar, slightly rough and curved substrates.

This adhesive is designed specifically for application at room temperature onto cardboard substrates.

Applications and use

The product is suitable for use where rigid or high caliper face material is required for functional reasons. This can include printed and folded 'header cards', 'banding' and 'reinforcement'. In areas of VIP tracking the product is used on uneven surfaces where bar codes may be distorted with conventional labels or where applied label must 'flag' clearly from the substrate for reasons of poor visibility and / or accessibility of scanning equipment.

Conversion & printing

Facestock can be printed by all conventional roll label technologies and is especially suited to offset litho process.

Special Approvals


The adhesive complies with the European food directives and legislations, FDA 175.105 and the German recommendations XXI as published by BfR. BfR (Bundesinstitut für Risikobewertung) is the German Federal Institute for Risk Assesment. The adhesive can be used in direct contact with dry and moist, non fatty foodstuffs.

Shelf life

Two years under storage conditions as defined by FINAT (20-25°C; 40-50%RH)

AV446

Fasson ® COATED CARD130 FSC - S2025N-BG40BR FSC



COATED CARD130 FSC

S2025N

BG40BR FSC

This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.

If you would like to make a suggestion or comment on this datasheet, please send an email to datasheet.mgmt@eu.averydennison.com

Avery Dennison Materials Group Europe

Willem Einthovenstraat 11 2342 BH Oegstgeest The Netherlands +31 (0)85 000 2000



Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes.

Avery Dennison products are warranted to be free of defects in material or workmanship for a period of one year from the date of shipment. Should a defect be communicated to Avery Dennison within that time frame, Avery Dennison will evaluate and determine the existence of the defect and further decide, at its sole discretion, to either replace the defective product without charge or compensate it with a credit note in such amount as Avery Dennison deems reasonable. Avery Dennison shall have no responsibility beyond the replacement value of the defective product nor shall in any way be liable or responsible for consequential or incidental damages.

ANY OTHER WARRANTY, WHETHER EXPRESS OR IMPLIED, OR WHETHER OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE OR OTHERWISE, SHALL BE EXCLUDED. NO WAIVER, ALTERATION, ADDITION OR MODIFICATION OF THE FOREGOING CONDITIONS SHALL BE VALID UNLESS MADE IN WRITING AND SIGNED BY AN EXECUTIVE OFFICER OF AVERY DENNISON.

©2013 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.

Issue date: December-2014