

### Facestock

A gloss white polyester film. The smooth surface is covered with a topcoat for very good ink anchorage.

Basis Weight	76 g/m <sup>2</sup>	ISO 536
Caliper	50 µm	ISO 534

### Adhesive

S333 is an excellent, general purpose industrial grade clear adhesive. Features low adhesive ooze, high initial tack and ultimate adhesion on high surface energy substrates.

### Liner

BG42 white, a supercalendered glassine paper.

Basis Weight	64 g/m <sup>2</sup>	ISO 536
Caliper	57 µm	ISO 534
Transparency	50 %	DIN 53147

### Laminate

Total Caliper	134 µm±10%	ISO 534
---------------	------------	---------

### Performance data

Initial Tack	9 N/25mm	FTM 9 Glass
Min. Application Temp.	5 °C	
Service temperature	-40°C to 150°C	
Peel Adhesion 90°	6 N/25mm	FTM 2 st.st. 24hr

Adhesive Type	Emulsion Acrylic	
Adhesive weight	26 g/m <sup>2</sup>	FTM12

### Adhesive Performance

Features low adhesive ooze, high initial tack and ultimate adhesion on high surface energy substrates.

### Applications and use

Transfer PET white TOP white is designed for conversion into identification, warning and tracking labels for durable goods such as automotive parts, electronic devices and home appliances.

This product is distinguished by the high chemical resistance of the thermal transfer print. For special requirements we strongly recommend application tests.

The adhesive S333 is globally available.

### Conversion & printing

Very good results can be achieved with thermal transfer printers equipped with conventional or near-edge print heads using resin ribbons. This product is qualified by EFI Jetrion and Durst for UV inkjet printing. Transfer PET white TOP can also be printed by all conventional roll label techniques, including flexo, UV letterpress, silkscreen.

For easy diecutting sharp corners should be avoided.


### Shelf life

Two years under storage conditions as defined by FINAT (20-25°C; 40-50%RH)

## AA669

### Fasson®

#### TRANSFER PET WHITE TOP - S333-BG42WH



TRANSFER PET WHITE TOP

S333

BG42WH

*This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.*

*If you would like to make a suggestion or comment on this datasheet, please send an email to [datasheet.mgmt@eu.averydennison.com](mailto:datasheet.mgmt@eu.averydennison.com)*

### Avery Dennison Materials Group Europe

Willem Einthovenstraat 11  
2342 BH Oegstgeest  
The Netherlands  
+31 (0)85 000 2000



#### Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>

©2016 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.