

Facestock

White polypropylene film with thermo-sensitive coating (black imaging).

Basis Weight	78 g/m ²	ISO 536
Caliper	100 µm	ISO 534

Adhesive

A general purpose permanent, rubber based adhesive.

Liner

BG40 brown, a supercalendered glassine paper.

Basis Weight	55 g/m ²	ISO 536
Caliper	49 µm	ISO 534

Laminate

Total Caliper	166 µm±10%	ISO 534
---------------	------------	---------

Performance data

Initial Tack	18 N/25mm	FTM 9 Glass
Peel Adhesion 90°	9 N/25mm	FTM 2 St.St.
Min. Application Temp.	0 °C	
Service temperature	-40°C to 70°C	

Adhesive Performance

The adhesive features excellent tack and adhesion on a wide variety of substrates, including apolar, slightly rough and curved substrates.

Particularly good performance at lower temperatures, e.g. labeling of chilled products.

Applications and use

A durable synthetic material with enhanced tear resistance and high sensitivity for use in a wide range of applications, including commercial tagging, wristbands, sport/game licensing, amusement pass, and ski lift tickets where short life or low contamination is common.

Conversion & printing

This thermo-sensitive product is designed for use in thermal printing systems at printing speeds up to 200 mm/sec. The product can be converted by all conventional roll conversion technologies including flexographic and UV letter press. However, due to the thermographic properties exposure above 50°C, it may cause premature imaging or discolouration. Inks containing alcohol or volatile organic solvents may cause discolouration of the thermosensitive coating. It is advisable to test inks and varnishes before conversion.

Special Approvals

The adhesive complies with the European food directives and legislations, FDA 175.105 and the German recommendations XXI as published by BfR. BfR (Bundesinstitut für Risikobewertung) is the German Federal Institute for Risk Assessment. The adhesive can be used in direct contact with dry and moist, non fatty foodstuffs.


Shelf life


One year under storage conditions as defined by FINAT (20-25°C; 40-50%RH)

AC628

Fasson®

THERMAL PP100 TOP WHITE - S2045N-BG40BR



THERMAL PP100 TOP WHITE	
----------------------------	--

S2045N	
--------	---

BG40BR	
--------	---

This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. The actual front and liner used might influence adhesive values. Further testing is always recommended.

If you would like to make a suggestion or comment on this datasheet, please send an email to datasheet.mgmt@eu.averydennison.com

2342 BH Oegstgeest
The Netherlands
+31 (0)85 000 2000



Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>

©2019 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.