



AC747

Fasson ®

**OVERLAM PET 25 MATT -
AL170-HF80**

**A matt, high clarity,
polyester
overlamination film
providing a premium
look of the finished
label and protection
against harsh
chemicals.**

Key features

Matt overlamination film with high clarity.

- > Good TT printability with selected ribbons.
- > Clear solvent acrylic adhesive featuring excellent chemical, UV and heat resistance.

> UL recognised.

Facestock

A matt, transparent overlaminating polyester.

Basis Weight	35 g/m ²	ISO 536
Caliper	25 µm	ISO 534

Adhesive

AL170 is a strong, permanent, solvent-based acrylate adhesive.

Liner

Hygroflat 80, a one side coated, bleached kraft paper.

Basis Weight	80 g/m ²	ISO 536
Caliper	78 µm	ISO 534

Laminate

Total Caliper	128 µm±10%	ISO 534
---------------	------------	---------

Performance data

Initial Tack	10 N/25mm	FTM 9 Glass
Min. Application Temp.	0 °C	
Service temperature	-80°C to 150°C	
Peel Adhesion 90°	9 N/25mm	FTM 2 st.st. 24hr

Adhesive Type	Solvent Acrylic
---------------	-----------------

Applications and use

This is used to create premium matt effect labels. The overlaminate protects the underlying label from abrasion and chemical attack.

Conversion & printing

Overlam PET 25 Matt does not have a topcoat and is usually not overprinted. When needed, it can take thermal transfer print. Due to the low calliper of this film, it cannot be dispensed by itself.

UL Recognition

This product meets the requirements as stated in UL 969 for indoor use. The UL file number is MH27538.


Shelf life

Two years under storage conditions as defined by FINAT (20-25°C; 40-50%RH)

AC747

Fasson ®

OVERLAM PET 25 MATT - AL170-HF80



OVERLAM PET 25 MATT

AL170

HF80

All data to be considered as typical values and subject to change without prior notice. The actual front and liner used might influence adhesive values. Further testing is always recommended.

If you would like to make a suggestion or comment on this datasheet, please send an email to datasheet.mgmt@eu.averydennison.com

Avery Dennison Materials Group Europe

Willem Einthovenstraat 11
2342 BH Oegstgeest
The Netherlands
+31 (0)85 000 2000



Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>

©2019 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.