

### Material

One side indigo top coated clear shrink PET. Up to 75% transversal shrinkage..

Basis Weight	66 g/m <sup>2</sup>	ASTM D 4321
Caliper	160 µm	ASTM D 4321
Tensile strength MD	6500 PSI	ASTM D882
Tensile strength CD	42000 PSI	ASTM D882
Elongation MD	500 %	ASTM D882
Elongation CD	50 %	ASTM D882
Shrinkage MD	< 3 %	99°, 10 sec.in water
Shrinkage CD	> 75 %	99°, 10 sec.in water

### Applications and use

For shrink sleeve applications eg. the labelling of bottle shaped or cylindric forms, top to bottom packaging and promotional packaging. Transversal shrinkage.

### Conversion & printing

The topcoating ensures full transfer of Electolnk in the one-shot transfer step in the Indigo Omnius press and related engines. The coating also provides excellent anchorage and scuff resistance of Electolnk based images.


### Shelf life

One year under storage conditions as defined by FINAT (20-25°C; 40-50%RH)

## AE667

## Fasson ®

## DIG INDI SR PET CL ULT50



DIG INDI SR PET CL ULT50

### Avery Dennison Materials Group Europe

Lammenschansweg 140

2321 JX Leiden

The Netherlands

+31 71 579 4100



This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.

If you would like to make a suggestion or report a mistake on this datasheet, please send an email to [datasheet.mgmt@eu.averydennison.com](mailto:datasheet.mgmt@eu.averydennison.com)

#### Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes.

Avery Dennison products are warranted to be free of defects in material or workmanship for a period of one year from the date of shipment. Should a defect be communicated to Avery Dennison within that time frame, Avery Dennison will evaluate and determine the existence of the defect and further decide, at its sole discretion, to either replace the defective product without charge or compensate it with a credit note in such amount as Avery Dennison deems reasonable. Avery Dennison shall have no responsibility beyond the replacement value of the defective product nor shall in any way be liable or responsible for consequential or incidental damages.

ANY OTHER WARRANTY, WHETHER EXPRESS OR IMPLIED, OR WHETHER OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE OR OTHERWISE, SHALL BE EXCLUDED. NO WAIVER, ALTERATION, ADDITION OR MODIFICATION OF THE FOREGOING CONDITIONS SHALL BE VALID UNLESS MADE IN WRITING AND SIGNED BY AN EXECUTIVE OFFICER OF AVERY DENNISON.

©2013 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.