Facestock

A bi-axially oriented bright cristaline holographic polypropylene film with a print-receptive top coat, laminated to paper.

Basis Weight 70 g/m 2 ISO 536 Caliper 60 μ m ISO 534

Adhesive

A general purpose permanent, rubber based adhesive.

Liner

BG40 brown, a supercalendered glassine paper.

Laminate

Total Caliper 130 µm±10% ISO 534

Performance data

Initial Tack 22 N/25mm FTM 9 Glass Peel Adhesion 90° 11 N/25mm FTM 2 St.St.

Min. Application Temp. 0 °C

Service temperature -40°C to 70°C

Adhesive Performance

The adhesive features excellent tack and adhesion on a wide variety of substrates, including apolar, slightly rough and curved substrates.

Particularly good performance at lower temperatures, e.g. labeling of chilled products.

Applications and use

Holographic labels are particularly eye catching and give brands an extra chance to catch the customer's attention, on very competitive markets. Traditionally used in cosmetics, they also fit the spirits and trendy beverage market.

Conversion & printing

The film can be printed by conventional printing techniques including Gravure, UV flexo and offset. For optimum ink adhesion a primer is advised and corona treatment recommended. Please consult your ink supplier for ink recommendations. The pattern range is made by cliches of different dimensions, therefore some lines can appear on the hologram. Two shimlines will appear, in cross-direction repeating after 720 mm.

Special Approvals


The adhesive complies with the European food directives and legislations, FDA 175.105 and the German recommendations XXI as published by BfR. BfR (Bundesinstitut für Risikobewertung) is the German Federal Institute for Risk Assesment. The adhesive can be used in direct contact with dry and moist, non fatty foodstuffs.

Shelf life

Two years under storage conditions as defined by FINAT (20-25°C; 40-50%RH)

AE740

Fasson ® HGFP CRISTALINE TOP - S2045N-BG40BR



HGFP CRISTALINE TOP

S2045N

BG40BR



This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.

If you would like to make a suggestion or comment on this datasheet, please send an email to datasheet.mgmt@eu.averydennison.com

Avery Dennison Materials Group Europe

Willem Einthovenstraat 11 2342 BH Oegstgeest The Netherlands +31 (0)85 000 2000



All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see http://terms.europe.averydennison.com

©2016 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery