

### Facestock

A matt white high-density polyethylene (HDPE) film with a smooth, absorbent, ink receptive topcoating.

Basis Weight	90 g/m <sup>2</sup>	ISO 536
Caliper	110 µm	ISO 534

### Adhesive

A special purpose permanent, rubber based adhesive.

### Liner

BG40 brown, a supercalendered glassine paper.

Basis Weight	56 g/m <sup>2</sup>	ISO 536
Caliper	49 µm	ISO 534

### Laminate

Total Caliper	192 µm±10%	ISO 534
---------------	------------	---------

### Performance data

Initial Tack	33 N/25mm	FTM 9 Glass
Peel Adhesion 90°	17 N/25mm	FTM 2 St.St.
Min. Application Temp.	-5 °C	
Service temperature	-40°C to 70°C	

### Adhesive Performance

The aggressive nature of the adhesive provides excellent performance on rough or difficult substrates such as rubber goods, shoes, rugs and carpets, as well as on packaging materials like cardboard, wood, fibre drums and plastic containers (e.g. HDPE and Polypropylene drums). In addition the adhesive has excellent performance at low temperature and on apolar substrates.

### Applications and use

Designed for use in very difficult application areas i.e. where surface is very rough and hence initial adherence surface contact is low. Typical applications can vary from shrink wrapped pallets to timber, rough metal castings and rough LDPE drums. These labels are often pre-printed, then overprinted with variable information at time of application.

### Special Approvals

The adhesive complies with the European food directives and legislations, FDA 175.105 and the German recommendations XXI as published by BfR. BfR (Bundesinstitut für Risikobewertung) is the German Federal Institute for Risk Assessment. The adhesive can be used in direct contact with dry, non fatty foodstuffs.


This material complies with BS 5609, Section two, Marine Immersion Test.




### Shelf life

One year under storage conditions as defined by FINAT (20-25°C; 40-50%RH)

## AF207

### Fasson ® TUFF - S445N-BG40BR



TUFF	
S445N	
BG40BR	

All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended. If you would like to make a suggestion or comment on this datasheet, please send an email to

Basis Weight	90 g/m <sup>2</sup>	ISO 536
Caliper	110 µm	ISO 534

#### Adhesive

A special purpose permanent, rubber based adhesive.

#### Liner

BG40 brown, a supercalendered glassine paper.

Basis Weight	56 g/m <sup>2</sup>	ISO 536
Caliper	49 µm	ISO 534

#### Laminate

Total Caliper	192 µm±10%	ISO 534
---------------	------------	---------

#### Performance data

Initial Tack	33 N/25mm	FTM 9 Glass
Peel Adhesion 90°	17 N/25mm	FTM 2 St.St.
Min. Application Temp.	-5 °C	
Service temperature	-40°C to 70°C	

#### Adhesive Performance

The aggressive nature of the adhesive provides excellent performance on rough or difficult substrates such as rubber goods, shoes, rugs and carpets, as well as on packaging materials like cardboard, wood, fibre drums and plastic containers (e.g. HDPE and Polypropylene drums). In addition the adhesive has excellent performance at low temperature and on apolar substrates.

#### Applications and use

Designed for use in very difficult application areas i.e. where surface is very rough and hence initial adherence surface contact is low. Typical applications can vary from shrink wrapped pallets to timber, rough metal castings and rough LDPE drums. These labels are often pre-printed, then overprinted with variable information at time of application.

#### Special Approvals

The adhesive complies with the European food directives and legislations, FDA 175.105 and the German recommendations XXI as published by BfR. BfR (Bundesinstitut für Risikobewertung) is the German Federal Institute for Risk Assessment. The adhesive can be used in direct contact with dry, non fatty foodstuffs.

This material complies with BS 5609, Section two, Marine Immersion Test.

#### Shelf life

One year under storage conditions as defined by FINAT (20-25°C; 40-50%RH)

[datasheet.mgmt@eu.averydennison.com](mailto:datasheet.mgmt@eu.averydennison.com)

#### Avery Dennison Materials Group Europe

Willem Einthovenstraat 11  
2342 BH Oegstgeest  
The Netherlands  
+31 (0)85 000 2000



**Warranty**

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>

©2016 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.