

### Material

A highly white and opaque polyester film which has been treated on both sides to promote adhesion to inks and lacquers.

Basis Weight	71 g/m <sup>2</sup>	ISO 536
Caliper	50 µm	ISO 534
Tensile Str. MD	14 kgf/mm <sup>2</sup>	ASTM D 882-83
Tensile Str. CD	17 kgf/mm <sup>2</sup>	ASTM D 882-83
Elongation MD	120 %	ASTM D 882-83
Elongation CD	120 %	ASTM D 882-83
Gloss	45 %	ASTM D 2457-90
Light Transmission	17 %	ASTM D 1003-77

### Applications and use

For tag applications where good chemical resistance to dilute acids and alkalis, concentrated sulphuric acid, greases, oil, fat and seawater. Also used for security cards, acces cards and multiple use tickets.

### Conversion & printing

The chemical adhesion pre-treat has a more permanent effect than corona treatment and does not modify the dyne level of the surface thus giving improved print definition and adhesion to most printing inks and industrial coatings. It can thus be printed with all common printing techniques, like flexo, UV letterpress or thermal transfer.


### Shelf life

One year under storage conditions as defined by FINAT (20-25°C; 40-50%RH)

## AG365

## Fasson®

## PET WHITE 2S-50



PET WHITE 2S-50

*This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. The actual front and liner used might influence adhesive values. Further testing is always recommended.*

*If you would like to make a suggestion or comment on this datasheet, please send an email to [datasheet.mgmt@eu.averydennison.com](mailto:datasheet.mgmt@eu.averydennison.com)*

### Avery Dennison Materials Group Europe

Willem Einthovenstraat 11  
2342 BH Oegstgeest  
The Netherlands  
+31 (0)85 000 2000

#### Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>



©2019 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.