

### Facestock

A white, spun-bonded polyolefin with exceptional tear resistance.

Basis Weight	75 g/m <sup>2</sup>	ISO 536
Caliper	205 µm	ISO 534

### Adhesive

A general purpose permanent, acrylic based adhesive.

### Liner

BG50 white, a supercalendered glassine paper. The liner is made from FSC® certified paper (FSC Mix Credit, chain-of-custody number: CU-COC-807907, Licence Code: C004451).

Basis Weight	78 g/m <sup>2</sup>	ISO 536
Caliper	68 µm	ISO 534

### Laminate

Total Caliper	297 µm±10%	ISO 534
---------------	------------	---------

### Performance data

Initial Tack	12 N/25mm	FTM 9 Glass
Peel Adhesion 90°	8 N/25mm	FTM 2 St.St.
Min. Application Temp.	5 °C	
Service temperature	-20°C to 80°C	

### Adhesive Performance

S692N is a clear permanent adhesive featuring excellent UV resistance and weatherability together with good adhesion performance, even on apolar substrates.

### Applications and use

Due to the high mechanical and chemical resistance of the face stock, the product is suitable for labels on containers, drums in the chemical industry, and for the production of durable tags for industrial and horticultural applications.

### Conversion & printing

Printing can be done in all the usual printing techniques. Avoid the use of large quantities of volatile solvents in the letterpress and offset processes. Polyamide and vinyl inks are preferred for flexo printing. For gravure printing, inks with cello-solve and acetone can be used. The 'milder' type of screen inks are recommended. Considering the variations in the face materials' caliper, it is recommended to limit larger solid printing areas in the print lay-out.


### Shelf life

Two years under storage conditions as defined by FINAT (20-25°C; 40-50%RH)

## AG405

## Fasson ®

## TYVEK75 - S692N INC-BG50WH FSC



TYVEK75

S692N

BG50WH FSC

*This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. The actual front and liner used might influence adhesive values. Further testing is always recommended.*

*If you would like to make a suggestion or comment on this datasheet, please send an email to [datasheet.mgmt@eu.averydennison.com](mailto:datasheet.mgmt@eu.averydennison.com)*

### Avery Dennison Materials Group Europe

Willem Einthovenstraat 11  
2342 BH Oegstgeest  
The Netherlands  
+31 (0)85 000 2000

#### Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>



©2019 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.

