

Facestock

A White uncoated, matt, smooth woodfree printing paper under-laminated. Wet strength and fungicidal treatments.

| | | |
|--------------|----------------------|---------|
| Basis Weight | 110 g/m ² | ISO 536 |
| Caliper | 123 µm | ISO 534 |

Adhesive

A general purpose permanent, rubber based adhesive for the wine industry.

Liner

BG45 white, a supercalendered glassine paper.

| | | |
|--------------|---------------------|-----------|
| Basis Weight | 70 g/m ² | ISO 536 |
| Caliper | 63 µm | ISO 534 |
| Transparency | 50 % | DIN 53147 |

Laminate

| | | |
|---------------|------------|---------|
| Total Caliper | 204 µm±10% | ISO 534 |
|---------------|------------|---------|

Performance data

| | | |
|------------------------|---------------|--------------|
| Initial Tack | 23 N/25mm | FTM 9 Glass |
| Peel Adhesion 90° | 12 N/25mm | FTM 2 St.St. |
| Min. Application Temp. | 5 °C | |
| Service temperature | -30°C to 70°C | |

Adhesive Performance

The adhesive features excellent tack and adhesion on a wide variety of substrates, including apolar, and slightly rough substrates.

Applications and use

This product is designed for Wine labelling, where extra extra water resistance is required. Due to its high stiffness it is not recommended for labelling on small diameters, neck labels in particular.

Conversion & printing

Printable by all conventional printing techniques. Due to open and textured nature of the facematerial, best results are in general from those techniques with maximum conformability of printing plate such as flexo and offset. Excellent results, in line with desired image, using offset or screen.

Special Approvals

The adhesive complies with the European food directives and legislations, FDA 175.105 and the German recommendations XXI as published by BfR. BfR (Bundesinstitut für Risikobewertung) is the German Federal Institute for Risk Assessment. The adhesive can be used in direct contact with dry and moist, non fatty foodstuffs.


Shelf life

Two years under storage conditions as defined by FINAT (20-25°C; 40-50%RH)

AL374

Fasson®

CENTAURE BLANC PLUS - S2047N-BG45WH



CENTAURE BLANC PLUS

S2047N

BG45WH

This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.

If you would like to make a suggestion or comment on this datasheet, please send an email to datasheet.mgmt@eu.averydennison.com

Avery Dennison Materials Group Europe

Willem Einthovenstraat 11
2342 BH Oegstgeest
The Netherlands
+31 (0)85 000 2000

Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery



ANY OTHER WARRANTY, WHETHER EXPRESS OR IMPLIED, OR WHETHER OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE OR OTHERWISE,

Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes.

Avery Dennison products are warranted to be free of defects in material or workmanship for a period of one year from the date of shipment. Should a defect be communicated to Avery Dennison within that time frame, Avery Dennison will evaluate and determine the existence of the defect and further decide, at its sole discretion, to either replace the defective product without charge or compensate it with a credit note in such amount as Avery Dennison deems reasonable. Avery Dennison shall have no responsibility beyond the replacement value of the defective product nor shall in any way be liable or responsible for consequential or incidental damages.

SHALL BE EXCLUDED. NO WAIVER, ALTERATION, ADDITION OR MODIFICATION OF THE FOREGOING CONDITIONS SHALL BE VALID UNLESS MADE IN WRITING AND SIGNED BY AN EXECUTIVE OFFICER OF AVERY DENNISON.

©2013 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.