

Facestock

A light weight white, woodfree, top coated thermal paper, with a black imaging thermosensitive coating providing good resistance to moisture, fat, oil for a short period of time. The facestock is made from FSC® certified paper (FSC Mix Credit, chain-of-custody number: CU-COC-807907, Licence Code: C004451).

Basis Weight	60 g/m ²	ISO 536
Caliper	66 µm	ISO 534
Max Print Speed	200 mm/sec	
Image Density (Typical)	1.3 odu	

Adhesive

A general purpose permanent, rubber based adhesive.

Liner

BG30 brown FSC, a supercalendered glassine paper.

Basis Weight	50 g/m ²	ISO 536
Caliper	46 µm	ISO 534

Laminate

Total Caliper	123 µm±10%	ISO 534
---------------	------------	---------

Performance data

Initial Tack	18 N/25mm	FTM 9 Glass
Peel Adhesion 90°	9 N/25mm	FTM 2 St.St.
Min. Application Temp.	0 °C	
Service temperature	-40°C to 60°C	

Adhesive Performance

The adhesive features excellent tack and adhesion on a wide variety of substrates, including apolar, slightly rough and curved substrates.

Particularly good performance at lower temperatures, e.g. labeling of chilled products.

Applications and use

This light weight Direct Thermal product is designed for use in transportation and logistics applications where a short term resistance to an assortment of chemicals, handling, plasticizers and very light moisture is required. Typical end use applications include courier, warehouse and process tracking. Particularly suited for use in hand-held mobile thermal printers. Long term contact with an assortment of chemicals or heavy moisture can cause potential image fading.

The liner is made from FSC® certified paper (FSC Mix Credit, chain-of-custody number: CU-COC-807907, Licence Code: C004451).

Conversion & printing

The product is primarily recommended for use in blank label applications. Though applications using conventional roll conversion technologies including flexographic and UV letterpress can be considered providing testing is completed for the compatibility of inks in the specific thermal printing units. Also, due to the thermographic properties, exposure above 50°C may cause premature imaging or discoloration. It is advisable to test inks and varnishes before conversion.

We generally recommend not to pre-print the label area that needs to be thermally printed.


The thinner liner requires more care taken in the die cutting process to avoid over cutting into the liner.

Special Approvals

AL747

Fasson®

THERMAL THIN 200LL FSC - S2045N- BG30BR FSC



THERMAL THIN 200LL FSC

S2045N

BG30BR FSC

This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.

If you would like to make a suggestion or comment on this datasheet, please send an email to datasheet.mgmt@eu.averydennison.com

The adhesive complies with the European food directives and legislations, FDA 175.105 and the German recommendations XXI as published by BfR. BfR (Bundesinstitut für Risikobewertung) is the German Federal Institute for Risk Assessment. The adhesive can be used in direct contact with dry and moist, non fatty foodstuffs.

Shelf life

One year under storage conditions as defined by FINAT (20-25°C; 40-50%RH)

Avery Dennison Materials Group Europe

Willem Einthovenstraat 11
2342 BH Oegstgeest
The Netherlands
+31 (0)85 000 2000

Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>



©2016 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.