

Material

A white, one side machine coated, solid bleached sulphate (SBS) board with semi-gloss appearance.

Basis Weight	190 g/m ²	ISO 536
Caliper	200 µm	ISO 534
Bending resistance L&W 15° 75 mN MD		ISO 2493
Bending resistance L&W 15° 35 mN CD		ISO 2493
ISO Brightness C / 2°	95 %	ISO 2470
CIE Whiteness D65/10°, Top	125	ISO 11475
Surface Smoothness PPS 10	.9 µm	ISO 8791-4
Gloss 75°	48 %	ISO 8254-1
Scott Bond	220 J/m ²	TAPPI 569

Applications and use

This card is suitable for garment tags, event tickets, furniture tags, door hangers and mailers. Other typical applications include brochures, covers for brochures and annual reports. Corporate graphics such as folders, business cards and invitations. Posters, calendars, menus, greeting cards and product cards.

Conversion & printing

This product is suitable for printing by letterpress, flexo (UV and waterbased) offset and screen processes. Variable imprinting with thermal transfer are also suitable for this product. Finishing techniques include embossing, film and foil laminating, varnishing, die cutting, folding, scoring and cutting.


Shelf life

One year under storage conditions as defined by FINAT (20-25°C; 40-50%RH)

AL808

Fasson®

MC PRIMECOAT CARD 1S-190



MC PRIMECOAT CARD 1S-190

This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.

If you would like to make a suggestion or comment on this datasheet, please send an email to datasheet.mgmt@eu.averydennison.com

Avery Dennison Materials Group Europe

Willem Einthovenstraat 11
2342 BH Oegstgeest
The Netherlands
+31 (0)85 000 2000

Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes.

Avery Dennison products are warranted to be free of defects in material or workmanship for a period of one year from the date of shipment. Should a defect be communicated to Avery Dennison within that time frame, Avery Dennison will evaluate and determine the existence of the defect and further decide, at its sole discretion, to either replace the defective product without charge or compensate it with a credit note in such amount as Avery Dennison deems reasonable. Avery Dennison shall have no responsibility beyond the replacement value of the defective product nor shall in any way be liable or responsible for consequential or incidental damages.



ANY OTHER WARRANTY, WHETHER EXPRESS OR IMPLIED, OR WHETHER OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE OR OTHERWISE, SHALL BE EXCLUDED. NO WAIVER, ALTERATION, ADDITION OR MODIFICATION OF THE FOREGOING CONDITIONS SHALL BE VALID UNLESS MADE IN WRITING AND SIGNED BY AN EXECUTIVE OFFICER OF AVERY DENNISON.

©2013 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.