

Material

C1S Paper 90g / 12 gr gum. Activation of sticking / sealing properties with water.

Basis Weight	102 g/m ²	ISO 536
Caliper	78 µm	ISO 534
Tensile strength MD	>8.0 daN/15mm	DIN 53455
Tensile strength CD	>4.0 daN/15mm	DIN 53455
Adhesive weight	12.0 +-10% g/m ² 0	
Bekk smoothness	>1200 sec	
Speed of stick	3 sec	0

Applications and use

This dry gummed paper adheres to a wide range of substrates including wood, glass, ceramic, bond- and kraft papers, cartons, plastics and various fabrics after re-moisturizing the adhesive.


Conversion & printing

The semi-gloss machine coated surface can be printed with a variety of printing processes such as offset litho, web fed offset, letterpress, gravure and flexogravure. Also dot matrix printing and thermal transfer printing is possible, but it is recommended to test this first.

Shelf life

One year under storage conditions as defined by FINAT (20-25°C; 40-50%RH)

AM595 Fasson® MC GUMMED 1S-100



MC GUMMED 1S-100

This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.

If you would like to make a suggestion or comment on this datasheet, please send an email to datasheet.mgmt@eu.averydennison.com

Avery Dennison Materials Group Europe

Willem Einthovenstraat 11
2342 BH Oegstgeest
The Netherlands
+31 (0)85 000 2000

Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes.

Avery Dennison products are warranted to be free of defects in material or workmanship for a period of one year from the date of shipment. Should a defect be communicated to Avery Dennison within that time frame, Avery Dennison will evaluate and determine the existence of the defect and further decide, at its sole discretion, to either replace the defective product without charge or compensate it with a credit note in such amount as Avery Dennison deems reasonable. Avery Dennison shall have no responsibility beyond the replacement value of the defective product nor shall in any way be liable or responsible for consequential or incidental damages.



ANY OTHER WARRANTY, WHETHER EXPRESS OR IMPLIED, OR WHETHER OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE OR OTHERWISE, SHALL BE EXCLUDED. NO WAIVER, ALTERATION, ADDITION OR MODIFICATION OF THE FOREGOING CONDITIONS SHALL BE VALID UNLESS MADE IN WRITING AND SIGNED BY AN EXECUTIVE OFFICER OF AVERY DENNISON.

©2013 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.