

Facestock

A clear bi-axially oriented, polypropylene film with a print-receptive topcoat.

Basis Weight	53 g/m ²	ISO 536
Caliper	58 µm	ISO 534

Adhesive

C3 is a transparent, dispersion-based removable, acrylic adhesive.

Liner

BG40 white, a supercalendered glassine paper.

Basis Weight	61 g/m ²	ISO 536
Caliper	54 µm	ISO 534

Laminate

Total Caliper	131 µm±10%	ISO 534
---------------	------------	---------

Performance data

Initial Tack	4 N/25mm	FTM 9 Glass
Peel Adhesion 90°	2.5 N/25mm	FTM 2 St.St.
Min. Application Temp.	0 °C	
Service temperature	-40°C to 100°C	

Adhesive Performance

C3 is a highly transparent adhesive with high ageing stability for removable labels, e.g. for cosmetics and pharmacy applications.

Applications and use

Applications are predominantly in market segments where rigid containers are used (e.g. Glass, PET). Due to fairly rigid nature of the film care should be taken with use on non-uniform surfaces and where a very high level of squeezability is desired. C3 removes clean from many substrates from polymeric (PET, PP, ABS, PS), fiberboard, aluminium, stainless steel, glass (not suitable for window labelling)

Conversion & printing

The modified acrylic based topcoating can be printed by conventional printing techniques including flexo, screen, offset, letterpress, silkscreen, gravure, and hot or cold foiling processes. UV, water-based and solvent-based inks can be used. The topcoat is designed for optimum ink adhesion. On-press corona treatment is not advised. The face material is suitable for Thermal Transfer printing. Exact inks, foils and ribbons should be specified by your ink/foil/ribbon supplier.

The material has excellent register properties especially when a high number of different colours are used.

Special Approvals



The adhesive complies with the European food directives and legislations, FDA 175.105 and the German recommendations XIV as published by BfR. BfR (Bundesinstitut für Risikobewertung) is the German Federal Institute for Risk Assessment. The adhesive can be used in direct contact with dry and moist, non fatty foodstuffs.

Shelf life

Two years under storage conditions as defined by FINAT (20-25°C; 40-50%RH)

AN060

Fasson® PP TOP CLEAR - C3-BG40WH



Avery Dennison Materials Group Europe

Lammenschansweg 140

2321 JX Leiden

The Netherlands

+31 71 579 4100



This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.

If you would like to make a suggestion or report a mistake on this datasheet, please send an email to datasheet.mgmt@eu.averydennison.com

Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes.

Avery Dennison products are warranted to be free of defects in material or workmanship for a period of one year from the date of shipment. Should a defect be communicated to Avery Dennison within that time frame, Avery Dennison will evaluate and determine the existence of the defect and further decide, at its sole discretion, to either replace the defective product without charge or compensate it with a credit note in such amount as Avery Dennison deems reasonable. Avery Dennison shall have no responsibility beyond the replacement value of the defective product nor shall in any way be liable or responsible for consequential or incidental damages.

ANY OTHER WARRANTY, WHETHER EXPRESS OR IMPLIED, OR WHETHER OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE OR OTHERWISE, SHALL BE EXCLUDED. NO WAIVER, ALTERATION, ADDITION OR MODIFICATION OF THE FOREGOING CONDITIONS SHALL BE VALID UNLESS MADE IN WRITING AND SIGNED BY AN EXECUTIVE OFFICER OF AVERY DENNISON.

©2013 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.