

Facestock

A cavitated white corona treated, bi-axially oriented, polypropylene film .

| | | |
|--------------|---------------------|---------|
| Basis Weight | 30 g/m ² | ISO 536 |
| Caliper | 40 µm | ISO 534 |

Adhesive

A general purpose permanent, acrylic based adhesive.

Liner

BG40 white, a supercalendered glassine paper.

| | | |
|--------------|---------------------|---------|
| Basis Weight | 61 g/m ² | ISO 536 |
| Caliper | 54 µm | ISO 534 |

Laminate

| | | |
|---------------|------------|---------|
| Total Caliper | 111 µm±10% | ISO 534 |
|---------------|------------|---------|

Performance data

| | | |
|------------------------|---------------|--------------|
| Initial Tack | 10 N/25mm | FTM 9 Glass |
| Peel Adhesion 90° | 6 N/25mm | FTM 2 St.St. |
| Min. Application Temp. | 5 °C | |
| Service temperature | -20°C to 80°C | |

Adhesive Performance

S692N is a clear permanent adhesive featuring excellent UV resistance and weatherability together with good adhesion performance, even on apolar substrates.

Applications and use

Applications are predominantly in market segments where rigid containers are used (e.g. Glass, PET). Due to fairly rigid nature of the film care should be taken with use on non-uniform surfaces and where a very high level of squeezability is desired

Conversion & printing

The corona treated face material can be printed by conventional printing techniques and is suitable for Thermal Transfer printing with specific ribbons. Exact inks, foils and ribbons should be specified by your ink/foil/ribbon supplier. On-press corona treatment is recommended for good ink adhesion. For optimum ink adhesion use of our top coated PP Films is recommended. The material has excellent register properties.

Special Approvals

The adhesive complies with the European food directives and legislations, FDA 175.105 and the German recommendations XIV as published by BfR. BfR (Bundesinstitut für Risikobewertung) is the German Federal Institute for Risk Assessment. The adhesive can be used in direct contact with dry, moist and fatty foodstuffs with a reduction factor 2.


Shelf life

Two years under storage conditions as defined by FINAT (20-25°C; 40-50%RH)

AN073

Fasson ®

PP40 CAVIT WHITE - S692N-BG40WH



PP40 CAVIT WHITE

S692N

BG40WH

This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.

If you would like to make a suggestion or comment on this datasheet, please send an email to datasheet.mgmt@eu.averydennison.com

Avery Dennison Materials Group Europe

Willem Einthovenstraat 11
2342 BH Oegstgeest
The Netherlands
+31 (0)85 000 2000

Warranty





Inspired Brands.
Intelligent World.™

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes.

Avery Dennison products are warranted to be free of defects in material or workmanship for a period of one year from the date of shipment. Should a defect be communicated to Avery Dennison within that time frame, Avery Dennison will evaluate and determine the existence of the defect and further decide, at its sole discretion, to either replace the defective product without charge or compensate it with a credit note in such amount as Avery Dennison deems reasonable. Avery Dennison shall have no responsibility beyond the replacement value of the defective product nor shall in any way be liable or responsible for consequential or incidental damages.

ANY OTHER WARRANTY, WHETHER EXPRESS OR IMPLIED, OR WHETHER OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE OR OTHERWISE, SHALL BE EXCLUDED. NO WAIVER, ALTERATION, ADDITION OR MODIFICATION OF THE FOREGOING CONDITIONS SHALL BE VALID UNLESS MADE IN WRITING AND SIGNED BY AN EXECUTIVE OFFICER OF AVERY DENNISON.

©2013 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.