

Facestock

A white bi-axially oriented polypropylene film with a specific topcoating for excellent transfer and anchorage of Electrolnk as used in the Indigo process, allowing a wide range of design and performance choices on rigid packaging and bottles.

Basis Weight	51 g/m ²	ISO 536
Caliper	50 µm	ISO 534

Adhesive

A special permanent, acrylic based adhesive, for the pharmaceutical industry.

Liner

BG40 white, a supercalendered glassine paper.

Basis Weight	61 g/m ²	ISO 536
Caliper	54 µm	ISO 534

Laminate

Total Caliper	126 µm±10%	ISO 534
---------------	------------	---------

Performance data

Initial Tack	11 N/25mm	FTM 9 Glass
Peel Adhesion 90°	6.5 N/25mm	FTM 2 St.St.
Min. Application Temp.	5 °C	
Service temperature	-20°C to 80°C	

Adhesive Performance

S692NP is a clear permanent adhesive developed for the pharmaceutical industry with lowest risk for migration. It has excellent UV resistance together with good adhesion performance, even on apolar substrates.

Applications and use

The product is used in a variety of labelling applications, when the advantages of digital printing: short runs, last minute changes, personalised layouts and fast turn-round full colour printing are required.

Typical applications include labels for use in the pharmaceutical industry, applications on small cylindrical containers, curved substrates and on other known substrates in the pharmaceutical industry.

Conversion & printing

The topcoating ensures full transfer of Electrolnk in the one-shot transfer step in the HP Indigo press and related engines. The surface also provides excellent anchorage and improved rub resistance of Electrolnk based images.

Care should be taken with the use of heat for drying or UV curing.

It is recommended to overvarnish or overlamine the product to protect the print.

Special Approvals

The adhesive complies with the European food directives and legislations, FDA 175.105 and the German recommendations XIV as published by BfR. BfR (Bundesinstitut für Risikobewertung) is the German Federal Institute for Risk Assessment. The adhesive can be used in direct contact with dry and moist, non fatty foodstuffs.


Shelf life

One year under storage conditions as defined by FINAT (20-25°C; 40-50%RH)

AO143

Fasson ®

DIG INDI PP LIGHT TOP WH - S692NP-BG40WH



DIG INDI PP LIGHT WHITE

S692NP

BG40WH

Avery Dennison Materials Group Europe**Lammenschansweg 140****2321 JX Leiden****The Netherlands****+31 71 579 4100**

This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.

If you would like to make a suggestion or report a mistake on this datasheet, please send an email to datasheet.mgmt@eu.averydennison.com

Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes.

Avery Dennison products are warranted to be free of defects in material or workmanship for a period of one year from the date of shipment. Should a defect be communicated to Avery Dennison within that time frame, Avery Dennison will evaluate and determine the existence of the defect and further decide, at its sole discretion, to either replace the defective product without charge or compensate it with a credit note in such amount as Avery Dennison deems reasonable. Avery Dennison shall have no responsibility beyond the replacement value of the defective product nor shall in any way be liable or responsible for consequential or incidental damages.

ANY OTHER WARRANTY, WHETHER EXPRESS OR IMPLIED, OR WHETHER OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE OR OTHERWISE, SHALL BE EXCLUDED. NO WAIVER, ALTERATION, ADDITION OR MODIFICATION OF THE FOREGOING CONDITIONS SHALL BE VALID UNLESS MADE IN WRITING AND SIGNED BY AN EXECUTIVE OFFICER OF AVERY DENNISON.

©2013 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.