

### Material

A clear polyester-faced laminated pouching material used in packaging of snack foods. Adhesive coated two layer laminate (PET 12μ SiOx/PE 50μ).

Basis Weight	63.3 g/m <sup>2</sup>	ISO 536
Caliper	62 μm	ISO 534
2% Secant Modulus MD	>830 N/mm <sup>2</sup>	DIN EN ISO 527 T 3
2% Secant Modulus MD	>850 N/mm <sup>2</sup>	DIN EN ISO 527 T 3
Elongation at break MD	>70 %	DIN 53455
Elongation at break CD	>65 %	DIN 53455
Flexural Modulus Fmax MD	>250 mN	SCAN P 29 / DIN 52 121
Flexural Modulus Fmax CD	>300 mN	SCAN P 29 / DIN 52 121
Tear Elmendorf MD	>0.25 N	DIN EN 21974
Tear Elmendorf CD	>0.35 N	DIN EN 21974
Tensile Stren. MD	>50 N/mm <sup>2</sup>	ISO 527-3
Tensile Stren. CD	>45 N/mm <sup>2</sup>	ISO 527-3
Oxygen Permeability (23°C; 50%RH)	0,3 - 0,5 cm <sup>3</sup> /m <sup>2</sup> /24 hr	ASTM D3985
Water Vapor Transmission Rate (38°C, 90% RH)	0,1 - 0,2 g/m <sup>2</sup> /24 hr	ASTM F1249
Sealing Strength	>30 N/15mm	DIN 52 529 @140°C/5bar/0.5sec
Coefficient of Friction Inside/Inside	0,10 - 0,25 μs	ASTM D1895
Coefficient of Friction Outside/Outside	0,30 - 0,50 μs	ASTM D1895

### Applications and use

Heatsealable Flexible packaging laminates for nuts and other oxygen sensitive salted snacks or general-purpose snack good applications. Clear PET with Nano coating providing reduced OTR.

### Conversion & printing

The clear corona treated PET face provides printability via Flexo.


### Shelf life

One year under storage conditions as defined by FINAT (20-25°C; 40-50%RH)

## AO603

## Fasson ®

## SNACK WEB CLEAR62 NANO



SNACK WEB CLEAR62  
NANO

*This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. The actual front and liner used might influence adhesive values. Further testing is always recommended.*

*If you would like to make a suggestion or comment on this datasheet, please send an email to [datasheet.mgmt@eu.averydennison.com](mailto:datasheet.mgmt@eu.averydennison.com)*

### Avery Dennison Materials Group Europe

Willem Einthovenstraat 11  
2342 BH Oegstgeest  
The Netherlands  
+31 (0)85 000 2000

#### Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>



©2019 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.

