

Material

SILVER SNACK WEB 52

Basis Weight	54 g/m ²	ISO 536
Caliper	52 µm	ISO 534
2% Secant Modulus MD	>1000 N/mm ²	DIN EN ISO 527 T 3
2% Secant Modulus CD	>1000 N/mm ²	DIN EN ISO 527 T 3
Elongation at break MD	>60 %	DIN 53455
Elongation at break CD	>55 %	DIN 53455
Flexural Modulus Fmax MD	>150 mN	SCAN P 29 / DIN 52 121
Flexural Modulus Fmax CD	>200 mN	SCAN P 29 / DIN 52 121
Tear Elmendorf MD	>0.15 N	DIN EN 21974
Tear Elmendorf CD	>0.35 N	DIN EN 21974
Tensile Stren. MD	>50 N/mm ²	ISO 527-3
Tensile Stren. CD	>45 N/mm ²	ISO 527-3
Oxygen Permeability (23°C; 50%RH)	0,5 - 1,0 cm ³ /m ² /24 hr	ASTM D3985
Water Vapor Transmission Rate (38°C, 90% RH)	0,1 - 0,2 g/m ² /24 hr	ASTM F1249
Sealing Strength	>30 N/15mm	DIN 52 529 @140°C/5bar/0. 5sec
Coefficient of Friction Inside/Inside	0,15 - 0,30 µs	ASTM D1895
Coefficient of Friction Outside/Outside	0,30 - 0,50 µs	ASTM D1895

Applications and use

Film faced 2 layer laminate for packaging of snacks.

Conversion & printing


The chemically treated PET face provides printability Flexo and offset with UV low migration inks. Statement of Practical Use: This product should be tested thoroughly under end-user conditions to ensure it meets the requirements of the specific application. This is particularly the case if the intended use is for food. Avery Dennison therefore request the client to do sufficient testing to make sure that the intended application does not cause any harm and is safe.

Shelf life

One year under storage conditions as defined by FINAT (20-25°C; 40-50%RH)

AO605

Fasson® SNACK WEB SILVER52



SNACK WEB SILVER52

This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.

If you would like to make a suggestion or comment on this datasheet, please send an email to datasheet.mgmt@eu.averydennison.com

Avery Dennison Materials Group Europe

Willem Einthovenstraat 11
2342 BH Oegstgeest
The Netherlands
+31 (0)85 000 2000

Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>



©2016 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.



Inspired Brands.
Intelligent World.™