



**AP062**

**Fasson ®**

**TRANSF PET MATT CHR  
PT12 - S8007-BG40WH  
FSC**

## Key features

- > Good TT printability.
- > Emulsion based general purpose adhesive.

- > UL recognised label material.

### Facestock

A matt finished metallic polyester film. The smooth surface is print treated to achieve good thermal transfer printability and ink anchorage.

Basis Weight	70 g/m <sup>2</sup>	ISO 536
Caliper	50 µm	ISO 534
Maximum Service Temperature	120 °C	

### Adhesive

S8007 is a clear permanent general purpose adhesive featuring good heat and UV resistance together with good adhesion performance.

### Liner

BG40 white, a supercalendered glassine paper.

Basis Weight	60 g/m <sup>2</sup>	ISO 536
Caliper	53 µm	ISO 534

### Laminate

Total Caliper	123 µm±10%	ISO 534
---------------	------------	---------

### Performance data

Initial Tack	7.5 N/25mm	FTM 9 glass
Min. Application Temp.	5 °C	
Service temperature	-40°C to 120°C	
Peel Adhesion 90°	7 N/25mm	FTM 2 st.st. 24hr
Adhesive Type	Emulsion Acrylic	
Adhesive weight	19 g/m <sup>2</sup>	FTM12

### Adhesive Performance

The adhesive is designed for labelling smooth surfaces with a high or medium surface energy like metals or plastics, for example ABS, Polystyrene, Polycarbonate and Nylon.

### Applications and use

The polyester film "Transfer PET matt chrome PT 12" was developed as a solution for price sensitive, low-demanding Durables applications, especially in the home appliances or electronics segments. It features good TT printability and chemical resistance.

The liner is made from FSC® certified paper (FSC Mix Credit, chain-of-custody number: CU-COC-807907, Licence Code: C004451).

### Conversion & printing

This material is engineered for thermal transfer printing. Best results can be achieved with resin ribbons. Conventional printing (flexo, UV letterpress or silkscreen) is not recommended, and the suitability has to be tested prior use. This product is qualified by Durst for UV inkjet printing.

For easy diecutting sharp corners should be avoided.

### UL Recognition


This product meets the requirements as stated in UL 969 for indoor use. The UL file number is MH27538.

### Shelf life

# AP062

## Fasson ®

### TRANSF PET MATT CHR PT12 - S8007-BG40WH FSC



TRANSF PET MATT CHR  
PT12

S8007

BG40WH

Two years under storage conditions as defined by FINAT (20-25°C; 40-50%RH)

All data to be considered as typical values and subject to change without prior notice. The actual front and liner used might influence adhesive values. Further testing is always recommended.  
If you would like to make a suggestion or comment on this datasheet, please send an email to [datasheet.mgmt@eu.averydennison.com](mailto:datasheet.mgmt@eu.averydennison.com)

## Appendix 1

### Appendix 1: Performance Data

Note: the following technical data should be considered representative or typical only and should not be used for specification purposes.

Peel Adhesion:

FTM1: 180°, 300 mm/min, dwell time: 48 hours

Surface	N/25mm
ABS	9,0
Aluminium	9,0
Automotive lacquered panels	7,5
Glass	10,0
HDPE	3,5
LDPE	3,0
PA6	9,0
Stainless Steel	17,0

Chemical Resistance:

The performance results are based on 4 hours immersions at room temperature unless otherwise noted. Samples were applied to the test panel and conditioned for 24 hours before immersion and evaluated immediately upon removal. Peel adhesion was measured according to FTM1.

Chemical	Test Substrate	N/25mm	Visual appearance	Edge Penetration (mm)
Ad Blue	Aluminium	7,8	No change	1
Biodiesel	Glass	9,8	No change	0
Bioethanol E85	Glass	8,6	No change	2
Brake Fluid	Glass	9,6	No change	0
Diesel	Glass	8,8	No change	0
Engine Oil	Glass	9,2	No change	0
Gasoline	Glass	7,3	No change	3
Heptane	Glass	7,0	No change	3
Water, distilled	Aluminium	8,0	No change	3

**Chemicals:** Ad Blue: Aral, Bioethanol E85: CropEnergies CropPower85, Brake Fluid: DOT 4 Synthetic (One Way)  
Diesel: TOTAL, Engine Oil: TOTAL quartz 700, 10 W 40, Gasoline: TOTAL Euro 95



## Thermal Transfer Printing:

### Printability – Physical Resistance

Flat head printers (tests were performed with the printer Zebra XII 140):

Ribbon	Settings speed energy		Print Quality	ANSI Grade	Scratch resistance	Tape resistance
Armor AXR7+	3	30	++	D <sup>1</sup>	++	++
Armor AXR8	3	30	++	F <sup>1</sup>	++	++
DNP R300	3	30	+	D <sup>1</sup>	++	++
DNP R510	3	30	o	F <sup>1</sup>	++	o
limak SP330	3	30	++	F <sup>1</sup>	++	+
ITW B324	4	30	++	D <sup>1</sup>	++	++
Ricoh B110CR	3	30	++	D <sup>1</sup>	++	++

Near edge printers (tests were performed with the printer Avery TTX 450 – Near Edge):

Ribbon	Settings	Print Quality	ANSI Grade	Scratch resistance	Tape resistance
Armor AXR 600	5 "/s	+	F <sup>1</sup>	++	o
Armor AXR 800	4 "/s	-	F <sup>1</sup>	++	o
Ricoh B120 E	8 "/s	++	F <sup>1</sup>	+	-

ANSI (American National Standards Institute) Grade: information about barcode quality

A: excellent B: good C: acceptable D: readable with difficulty F: fail

<sup>1</sup>The print quality is good, but due to the reflection of metallised films the contrast is low

++: excellent +: good o: acceptable -: poor

### Chemical Resistance

The printed samples were wetted on the surface with a soft clean cotton cloth soaked in the test solution by wiping 10 times back and forth with light pressure. After 5 seconds they were dried with a clean dry soft cloth.

After 15 minutes the evaluation took place.

	AXR7+	AXR8	R300	R510	SP33 0	B324	B110 CR	AXR 600	AXR 800	B120 E
Ad Blue	+	+	+	+	+	+	+	+	+	+
Anti-Freeze	+	+	+	+	+	+	+	+	+	+
Biodiesel	+	+	+	+	o	+	+	-	-	-
Bioethanol E85	-	+	+	+	o	-	+	-	-	-
Brake fluid	-	+	o	+	o	-	+	-	-	-
Cleaner solvent	o	+	+	+	-	o	+	-	-	-
Engine oil	+	+	+	+	+	+	+	-	-	-
Gasoline	-	-	-	o	-	-	-	-	-	-
Hard wax polish	-	+	o	+	o	-	+	-	-	-
Isopropanol	o	+	+	+	o	-	+	-	-	-
Spirit	-	+	+	+	o	-	+	-	-	-

+: good (no change) o: acceptable (minor change, still readable) -: poor

### Chemicals:

Ad Blue: Aral, Anti-Freeze: Speedfrost "Speedfroil" 1:1 in water, Bioethanol E85: CropEnergies CropPower85

Brake Fluid: DOT 4 Synthetic (One Way), Cleaner Solvent: "Caramba" Cold Cleaner, Engine Oil: TOTAL quartz 700, 10 W 40

Gasoline: TOTAL Euro 95, Hard Wax Polish: „Nigrin“ Hard Wax Polish

## Appendix 2: Compliance Data

### UL – Underwriters Laboratories

File Number: MH27538

This material is UL recognized for exposure indoors to high humidity or occasional exposure to water.

Substrate	Minimum Temperature (°C)	Maximum Temperature (°C)
Acrylic paint	-40	+150
Acrylic powder paint	-40	+150
Alkyd paint	-40	+150
Aluminum	-40	+150
Epoxy paint	-40	+150
Epoxy powder paint	-40	+150
Galvanized steel	-40	+150
Polyester powder paint	-40	+150
Polyurethane powder paint	-40	+150
Stainless steel	-40	+150
Acrylonitrile butadiene styrene (ABS)	-40	+100
Glass	-40	+100
Nylon – Polyamide	-40	+100
Polybutylene terephthalate (PBT)	-40	+80
Polycarbonate	-40	+80
Polystyrene (PS)	-40	+80
Polyvinyl chloride (PVC)	-40	+80
Polypropylene (PP)	-40	+60

The UL certification includes the printing with the following thermal transfer ribbons:

Armor “AXR-7+”, AXR600”, “AXR8”, DNP “R300”, “R510”, “TR6075”, limak “SP-330”, “SP-990”, ITW “B324”, “B325”, Ricoh “B110CR” and “B120E”.

**Avery Dennison Materials Group Europe**

Willem Einthovenstraat 11  
2342 BH Oegstgeest  
The Netherlands  
+31 (0)85 000 2000

**Warranty**

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>



©2019 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.