

Facestock

White, 1-side top-coated matte finished, HDPE-crosslaminated, extreme resistance to tear, puncture and tear propagation. It consists of multiple layers of oriented film, extrusion laminated to each other

Basis Weight	153 g/m ²	ISO 536
Caliper	175 µm	ISO 534

Adhesive

An extra permanent, acrylic based adhesive.

Liner

BG55WH, a white supercalendered glassine paper.

Basis Weight	90 g/m ²	ISO 536
Caliper	78 µm	ISO 534

Laminate

Total Caliper	284 µm±10%	ISO 534
---------------	------------	---------

Performance data

Initial Tack	23 N/25mm	FTM 9 Glass
Peel Adhesion 90°	15 N/25mm	FTM 2 St.St.
Min. Application Temp.	5 °C	
Service temperature	-40°C to 90°C	

Adhesive Performance

S700 is a reinforced permanent acrylic based adhesive with very good initial tack and adhesion to a wide range of substrates.

Applications and use

Nothing
Special care should be given during dispensing around the gum free area

Conversion & printing

The topcoating allows the use of the following printing technologies: Thermal Transfer, Flexo Standard, Flexo UV, Offset UV, Screenprinting
The special product lay-out could have an influence on conversion speed


Shelf life

Two years under storage conditions as defined by FINAT (20-25°C; 40-50%RH)

AQ354

Fasson ®

VALERON175 TOP WHITE - S700 SGP-BG55WH


VALERON175
S700
BG55WH

Avery Dennison Materials Group Europe

Lammenschansweg 140
2321 JX Leiden
The Netherlands
+31 71 579 4100



This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.

If you would like to make a suggestion or report a mistake on this datasheet, please send an email to datasheet.mgmt@eu.averydennison.com

Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes.

Avery Dennison products are warranted to be free of defects in material or workmanship for a period of one year from the date of shipment. Should a defect be communicated to Avery Dennison within that time frame, Avery Dennison will evaluate and determine the existence of the defect and further decide, at its sole discretion, to

ANY OTHER WARRANTY, WHETHER EXPRESS OR IMPLIED, OR WHETHER OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE OR OTHERWISE, SHALL BE EXCLUDED. NO WAIVER, ALTERATION, ADDITION OR MODIFICATION OF THE FOREGOING CONDITIONS SHALL BE VALID UNLESS MADE IN WRITING AND SIGNED BY AN EXECUTIVE OFFICER OF AVERY DENNISON.

©2013 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are

either replace the defective product without charge or compensate it with a credit note in such amount as Avery Dennison deems reasonable. Avery Dennison shall have no responsibility beyond the replacement value of the defective product nor shall in any way be liable or responsible for consequential or incidental damages. trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.