

### Material

A matt, white, plain PE-HD film with an uncoated surface on both sides. Ideal for tag applications requiring direct food contact and high tear strength.

Basis Weight	129 g/m <sup>2</sup>	ISO 536
Caliper	120 µm	ISO 534
Tensile strength MD	27 N/mm <sup>2</sup>	DIN 53455
Tensile strength CD	20 N/mm <sup>2</sup>	DIN 53455
Elongation MD	650 %	DIN 53455
Elongation CD	600 %	DIN 53455
Opacity	88 %	DIN 53146
Whiteness ISO	92 %	ISO 2470
Tear Strength MD	110 gm/mm	ASTM D-1922
Tear Strength CD	220 gm/mm	ASTM D-1922

### Applications and use

This product is ideal for applications where durability, strength, moisture, grease and chemical resistance are required.

### Conversion & printing

The product can be converted by all conventional roll conversion technologies including: Letterpress, Offset, Screenprinting, UV flexo and Water-based flexo. This product is also suitable for variable information printing in: Thermal Transfer printing systems.


### Shelf life

One year under storage conditions as defined by FINAT (20-25°C; 40-50%RH)

## AT515

## Fasson®

### SYNTHETIC PAPER 130



SYNTHETIC PAPER 130



*This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. The actual front and liner used might influence adhesive values. Further testing is always recommended.*

*If you would like to make a suggestion or comment on this datasheet, please send an email to [datasheet.mgmt@eu.averydennison.com](mailto:datasheet.mgmt@eu.averydennison.com)*

### Avery Dennison Materials Group Europe

Willem Einthovenstraat 11  
2342 BH Oegstgeest  
The Netherlands  
+31 (0)85 000 2000

#### Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>



©2019 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.